

Thermochimica Acta 327 (1999) 39-46

thermochimica acta

Effect of MgO-doping on solid-solid interactions in $MoO₃/Al₂O₃$ system

H.G. El-Shobaky^{a,*}, M. Mokhtar^b, A.S. Ahmed^a

^aChemistry Department, Faculty of Science, Cairo University, Cairo, Egypt **b** Department of Physical Chemistry, National Research Center, Dokki, Cairo, Egypt

Received 21 October 1998; accepted 25 November 1998

Abstract

The effect of MgO-doping (2–10 mol%) on solid–solid interactions and phase transformation process in MoO₃/Al₂O₃ system were studied using thermogravimetry and X-ray diffraction (TG, DTG and XRD) techniques. The proportions of molybdena expressed as weight percent were 12.36, 22.01 and 41.37. The results obtained showed that the MgO-doping promoted the solid–solid interaction taking place at 500° C between Al₂O₃ and MoO₃ to produce Al₂(MoO₄)₃. However, MgO interacts readily with MO_3 at temperatures starting from 500° C yielding MgMoO₄ which remains stable even when heating at 1000 $^{\circ}$ C. The produced Al₂(MoO₄)₃ decomposed at temperatures starting from 800 $^{\circ}$ C producing α -Al₂O₃ and MoO₃, a portion of which sublimed and the other portion dissolved in alumina matrix forming $MoO₃-Al₂O₃$ solid solution. MgOdoping decreased slightly the solubility of MoO₃ in Al₂O₃. The promotion of Al₂(MoO₄)₃ formation at 500^oC and the decrease in the solubility of MoO₃ in Al₂O₃ by MgO have been attributed to dissolution of a small portion of MgO in the MoO₃ lattice with subsequent increase in the mobility of Mo⁶⁺ ions. The promotion effect of magnesia towards $Al_2(M_0O_4)$ ₃ formation and dissolution of MO_3 in Al_2O_3 solid are relatively small when compared to the observed effects reported in the case of Li₂Odoping of MoO₃/Al₂O₃ system. The limited effect of MgO-doping has been attributed to a limited solubility of MgO in MoO₃/ AI_2O_3 system due to the formation of MgMoO₄. \odot 1999 Elsevier Science B.V. All rights reserved.

Keywords: Solid-Solid interactions; MgO-doping $MoO₃/Al₂O₃$ system; TG; XRD

1. Introduction

Molybdenum oxides loaded on an active Al_2O_3 support are one of the most important solid catalysts [1-5]. The supported catalysts are usually prepared by impregnation of an alumina support from an aqueous solution of ammonium molybdate followed by thermal treatment at suitable temperatures.

The heating of physical mixture of crystalline MoO₃ and γ -Al₂O₃ at 400^oC for about 24 h resulted in the disappearance of all X-ray diffraction lines of $MoO₃$ due to the formation of two-dimensional $\text{Al}_2(\text{MoO}_4)_3$ film covering the surface of Al_2O_3 particles [6±8]. The increase in calcination temperature of $MoO₃/Al₂O₃$ to $\geq 500^{\circ}C$ enhances the surface and bulk mobilities of $MoO₃$, leading to well-crystallized $Al_2(M_0O_4)_3$ phase [9,10].

The metal-support interactions in the $MoO₃/Al₂O₃$ system could be influenced by doping with certain foreign cations such as Zn^{2+} , Ga^{3+} , Ge^{4+} , Li^+ and $Na⁺$ [3,4,11,12]. This influence may result from modification in the mobility of Mo^{6+} ions in the MoO₃

^{*}Corresponding author.

^{0040-6031/99/\$ -} see front matter \odot 1999 Elsevier Science B.V. All rights reserved. PII: S0040-6031(98)00657-1

lattice. It has been reported that doping of $MoO₃/$ Al_2O_3 mixed solids either with Li_2O [11] or Na₂O [12] enhanced metal-support interactions producing $Al₂(MoO₄)₃ phase.$

The present investigation reports a study of MgOdoping on solid-solid interactions in the $MoO₃-Al₂O₃$ system using TG and X-ray diffraction techniques. These techniques permitted us to clarify the effect of MgO-doping in the thermal behaviour of $MoO₃/Al₂O₃$ mixed solids subjected to thermal treatment at temperatures up to 1000° C and to identify the different crystalline phases produced by heating the mixed solids at various temperatures.

2. Experimental

2.1. Materials

A known mass of $Al(OH)_3$, analytical grade supplied by BDH, was impregnated with ammonium paramolybdate (BDH) solutions containing three different proportions of $(NH_4)_6Mo_7O_{24}$ 4H₂O. The proportions of ammonium molybdate were calculated so that the molar compositions of the calcined materials were $0.1MoO₃:Al₂O₃, 0.2MoO₃:Al₂O₃$ and $0.5MoO₃:$ Al_2O_3 . The impregnated materials were dried at 120 $\rm ^{\circ}C$, then calcined at 500 $\rm ^{\circ}C$, 700 $\rm ^{\circ}C$, 900 $\rm ^{\circ}C$ and 1000° C. The magnesium oxide doping was effected by treating the dried impregnated materials with an aqueous $Mg(NO₃)₂$ solution prior to the calcination. The time of heating of pure and doped materials was fixed for 5 h, and the amount of magnesium were 2, 4 and 10 mol% MgO, respectively, (with respect to the sum of Al_2O_3 and MoO_3). The prepared mixed solid specimens were designated as AlMo-I, AlMoI-2MgO, AlMo-I-4MgO, AlMO-I-10MgO, AlMo-II, AlMo- $II-2MgO$, $AlMo-II-4MgO$, $AlMo-II-10MgO$, AlMo-III, AlMo-III-4MgO and Al Mo-III-10MgO. The nominal molar compositions of the calcined mixed solids were $0.1MoO₃:Al₂O₃$ (I), $0.2MoO₃:$ Al_2O_3 (II) and $0.5MoO_3$: Al_2O_3 (III) and contained 12.4, 22.01 and 41.37 wt% $MoO₃$, respectively. $Al(OH)_{3}$ was used as a starting support material due to its decomposition during the thermal transformation of molybdate (into molybdena) which may provide chances for solid-solid interactions that was not attainable on using Al_2O_3 as a support.

2.2. Techniques

TG and DTG analyses of various uncalcined materials were carried out using a Perkin-Elmer (DT-7 Unix system) thermal analyser. A 18 mg solid portion was taken in each TG measurement. The reference material was α -Al₂O₃ (corundum). The rate of heating was kept as 10° C min⁻¹ and all the measurements were carried out in a current of N_2 flowing at 50 cm³ min⁻¹.

The X-ray powder diffraction patterns of the various calcined samples were measured using Nippon denshi kagaku. The patterns were run with nickel-filtered Cu K α radiation (λ =1.5405 Å) at 40 kV and 30 mA at a scanning rate of $2\theta = 8^{\circ} \text{min}^{-1}$.

3. Results and discussion

3.1. Thermal behaviour of pure and doped materials

TG and DTG curves of various pure and doped materials are summarized in Table 1. Representative TG and DTG curves are given in Figs. 1 and 2 for AlMo-II and AlMo-III doped with 10 mol% MgO. The recorded TG curves of the tested materials consist of seven successive mass loss processes. The first step extended between room temperature and 130° C and corresponds to departure of the physiosorbed water, while the second one extended between 130° C and 186° C indicates the removal of water of crystallization. The third and fourth steps were found between 186 $-$ 217 \degree C and 217 $-$ 283.9 \degree C, respectively. These steps characterize the decomposition of $Al(OH)₃$, $(NH_4)_{6}Mo_{7}O_{24}$ and $Mg(NO_3)_{2}$ producing the corresponding oxides according to

$$
(NH4)6Mo7O24 + Al(OH)3 + Mg(NO3)2\n\rightarrow 7MoO3 + 1/2 Al2O3 + MgO + 2NO2\n+6NH3 + 4.5H2O + 1/2 O2... (1)
$$

Details of the mechanism of thermal decomposition of ammonium molybdate yielding $MoO₃$ have been given elsewhere [9]. The fifth and sixth steps extended were between $450-550^{\circ}$ C and $550-800^{\circ}$ C, respectively. These steps might correspond to the removal of strongly bound hydroxyl groups and the last traces of these groups from alumina matrix. The last step

^aThe data of this column were computed by substracting the sum of the data of columns four and six from those of column five.

Fig. 1. TGA and DTG curves of uncalcined AlMo-II-10 MgO.

Fig. 2. TGA and DTG of uncalcined AlMo-III-10MgO sample.

extended between $800-1000^{\circ}$ C characterize the sublimation of some of the molybdena produced.

The values of mass loss due to heating at the temperature range $100-800^{\circ}$ C for the various samples were given in column two of Table 1. The theoretical mass loss accompanying the thermal decomposition of the tested materials producing the corresponding oxides according to Eq. (1) were calculated and given in column three of Table 1. The values given in the columns two and three are close to each other for the different investigated mixed solid samples which indicates the thermal stability of $MoO₃$ produced up to 800° C. The total weight loss accompanying the thermal treatment at $800-1000^{\circ}$ C were calculated for each sample and the values obtained are given in column four of Table 1. It is seen from Table 1 (column four) that the weight loss decreases progressively as a function of the amount of MgO added. This might indicate that the MgO present hinders the sublimation of $MoO₃$ to an extent proportional to its amount present. This hinderance could be attributed to a possible decrease in the mobility of the molybdena species or formation of $MgO-MoO₃$ compounds which are thermally stable at 1000° C. The formation of such compounds will be identified by XRD investigation given in the next section of this paper.

3.2. XRD investigation of various solids

Preliminary experiments showed that the thermal decomposition of ammonium molybdate in air at 500- 700° C resulted in the formation of well-crystallized orthorombic $MoO₃$ which sublimes completely by heating at 800° C.

X-ray differactograms of pure and doped mixed solids preheated in air at 500° C, 700° C, 900° C and 1000° C and those of pure Al(OH)₃ calcined at 500– 1000° C were determined. Table 2 lists the different phases present in various calcined solids. Representative differactograms of pure and doped AlMo-II and AlMo-III samples are given in Figs. 3 and 4.

It is seen from Table 2 that Al_2O_3 heated at 500– 700° C is amorphous in nature. While that calcined at 800 \degree C consists of poorly crystalline γ -Al₂O₃. The Xray diffractograms of pure Al_2O_3 preheated at 900 $^{\circ}$ C and 1000° C, not given, include the diffraction lines characteristic for κ -Al₂O₃ for the solids calcined at 900 \degree C and κ -Al₂O₃ together with a minute amount of

Fig. 3. X-ray diffractograms of pure and doped AlMo-III samples precalcined at 500°C: (1) MoO₃, (2) γ -Al₂O₃, (4) MgMoO₄, (5) $\text{Al}_2(\text{MoO}_4)_3$.

 α -Al₂O₃ (corundum) phase for the solid sample preheated at 1000° C. These results are in agreement with those published before [13,14]. Table 2 reveals that the pure and MgO-doped mixed oxide solid samples calcined at 500 $^{\circ}$ C are composed of γ -Al₂O₃ while that preheated at 700° C consists of κ -Al₂O₃ and that calcined at 900 $^{\circ}$ C and 1000 $^{\circ}$ C constitute of α - Al_2O_3 phase except the doped AlMo-I sample calcined at 900° C. This particular sample consists of a mixture of α -, γ - and θ -aluminas. From the above results it can be concluded that $MoO₃$ catalyses the crystallization process of Al_2O_3 . In fact, the complete transformation of pure Al_2O_3 specimen into the α form requires thermal treatment at elevated temperatures >1200 \degree C [14-16], or the presence of certain foreign oxides such as NiO [17], V_2O_5 [18], Co_3O_4 [19] and CuO [20]. These oxides enhance the crystallization process of alumina into α -Al₂O₃ (corundum) phase. In the present work the role of $MoO₃$ in catalysing the crystallization of Al_2O_3 into α -alumina like the above oxides is clear.

Inspection of the results obtained for pure and doped mixed oxide solids calcined at 500° C revealed that:

- 1. All the tested pure and mixed oxide solids consisted of $MoO₃$ phase.
- 2. Doping of AlMo-I and AlMo-II with 10% MgO resulted in stimulating an interaction between MgO and $MoO₃$ yielding $MgMoO₄$ according to

$$
MgO + MoO3 \stackrel{500^{\circ}C}{\rightarrow} MgMoO4... \tag{2}
$$

3. Doping of AlMo-III specimen with 10% MgO led to the formation of $MgMoO₄$ and aluminium molydate which takes place according to

Fig. 4. X-ray diffractograms of pure and doped AlMo-II and AlMo-III samples precalcined at 700°C: (3) κ -Al₂O₃, (4) $MgMoO₄, (5) Al₂(MoO₄)₃.$

$$
3MoO_3 + Al_2O_3 \overset{500°C}{\underset{MgO}{\longrightarrow}} Al_2(MoO_4)_3 \ldots \eqno{(3)}
$$

The later reaction clarifies the role of MgO in enhancing the solid-solid interaction between Al_2O_3 and $MoO₃$.

It can be expected that this role arises from dissolution of a small portion of MgO in $MoO₃$ lattice leading to an increase in the mobility of molybdenum ions. The fact that $MgMoO₄$ was formed in the case of AlMo-I (containing 12.36 wt\% MO_3) and $Al₂(MoO₄)₃$ was observed in the case of AlMo-III (containing 41.37 wt\% MoO₃) might indicate that MgO-MoO₃ interaction takes place prior to Al_2O_3 - $MoO₃$ one. From the above results it can be concluded that a portion of MgO dissolved in $MoO₃$ lattice enhances the interaction between Al_2O_3 and MoO_3 . The other portion of MgO reacts readily with $MoO₃$ and the MgO-MoO₃ interaction is easier than Al_2O_3 - $MoO₃$ one.

Analyses of the results given in Table 2 for the pure and doped mixed oxide solids preheated in air at 700° C showed that:

- 1. For AlMo-I there are no diffraction lines characteristic for free $MoO₃$ or $Al₂(MoO₄)₃$ phases which might indicate that $MoO₃$ interacted with $Al₂O₃$ yielding an amorphous $Al₂(MoO₄)₃$.
- 2. Doping of AlMo-I with 10% MgO resulted in the formation of well-crystallized $MgMoO₄$. The formation of mangnesium molybdate must not be accompanied by any change in weight.
- 3. Pure AlMo-II consists of $\text{Al}_2(\text{MoO}_4)_3$, while AlMo-II-10MgO consists of MgMoO₄ only. The disappearance of the diffraction lines of $Al₂$ - $(MoO₄)₃$ in the case of the doped mixed oxide solid sample calcined at 700° C reveals that $MgO-MoO₃$ interaction is more favourable, easier and prior to Al_2O_3 -MoO₃ interaction taking place at 700° C. These results are in agreement with those obtained in case of solids calcined at 500° C.
- 4. Pure AlMo-III mixed solid samples consisted of $Al₂(MoO₄)₃ phase, while those doped with 10%$ MgO was composed of a mixture of $MgMoO₄$ and $Al₂(MoO₄)₃$.

These results showed that $Mgo-MoO₃$ interaction is more favourable than Al_2O_3 -MoO₃ interaction and when takes place it goes to completion.

Inspection of results concerning the phases present in pure and doped solids calcined at 900° C and 1000° C showed that:

- 1. The diffraction patterns of all pure and mixed oxide solids reveal the absence of all diffraction lines characteristic for $Al_2(M_0O_4)_3$ indicating its decomposition into alumina phase.
- 2. All doped mixed oxide solids $(2-10 \text{ mol\%})$ contain MgMoO4 beside alumina phases. The obtained results indicate that $Al_2(MoO_4)_3$ decomposed at

temperature $\geq 800^{\circ}$ C and MgMoO₄ is thermally stable even when heated up to 1000° C.

From the XRD results the role of MgO in the enhancement of $Al_2(M_0O_4)_3$ formation at 500°C is evident. However, the amount of MgO dissolved in $MoO₃$ lattice might be small because of the chemical affinity towards interaction with $MoO₃$ yielding MgMoO4. On this basis, the calculation of the amount of $MoO₃$ reacting with MgO is given in Table 1 (column six) neglecting the amount of MgO dissolved in $MoO₃$ lattice.

Finally, doping of $MoO₃/Al₂O₃$ system with MgO led to two solid-solid interactions, the first reaction takes place between MgO and $MoO₃$ and the second occurs between Al_2O_3 and MoO_3 . The first reaction is more easier and takes place prior to the second one so, it can be assumed that $MgO-MoO₃$ interaction goes to completion. The amount of $MoO₃$ consumed in $MgMoO₄$ formation increases as a function of MgO content as shown in Table 1 (sixth column). Therefore, the amount of $MoO₃$ consumed in the formation of $\text{Al}_2(\text{MoO}_4)$ ₃ decreases by increasing the amount of dopant oxide present.

Aluminium molybdate decomposes at temperatures starting from 800° C yielding MoO₃, a portion of which sublimed (cf Table 1 column four) and the other one dissolved in Al_2O_3 matrix (cf. Table 1) column seven). It is seen from the last column of Table 1 that MgO-doping (10 mol%) of $MoO₃/Al₂O₃$ system brought about a small decrease in the amount of $MoO₃$ dissolved in $Al₂O₃$ lattice (it decreases from 7.8 to 6.8 wt% $MoO₃$ in the case of AlMo-II and from 16.08 to 13.6 wt% $MoO₃$ in the case of AlMo-III). This effect is much more pronounced in the case of $Li₂O$ doping of the same system [11]. In fact, it has been reported by El-Shobaky et al. [11] that $Li₂O$ (6 mol%) doping of $MoO₃/Al₂O₃$ system containing 22.01 wt% $MoO₃$ (which corresponds to AlMo-II) resulted in the decrease of amount of $MoO₃$ dissolved in Al_2O_3 matrix, forming solid solution, from 7.1 to 2.5 wt% $MoO₃$. The comparison of MgO doping with $Li₂O$ doping of $MoO₃/Al₂O₃$ system reflects the limited role of MgO in enhancing the sublimation of $MoO₃$ dissolved in $Al₂O₃$ matrix. This limited role might be discussed in terms of the limited amount of MgO contributing in the formation of $MgO-MoO₃$ solid solution.

4. Conclusions

The main conclusions that can be derived from the obtained results are as follows:

- 1. Doping of $MoO₃/Al₂O₃$ mixed solids with MgO enhance solid-solid interaction at 500° C to form $Al₂(MoO₄)₃$.
- 2. MgO interact readily with $MoO₃$ at temperatures starting from 500° C producing MgMoO₄ which remain thermally stable even by heating at 1000° C.
- 3. Aluminium molybdate decomposed at temperature \geq 800°C giving α -Al₂O₃ and MoO₃, a portion of which sublimed and the other portion dissolved in aluminium lattice forming $MoO₃-Al₂O₃$ solid solution.
- 4. MgO-doping decreased the solubility of $MoO₃$ in alumina support material to an extent proportional to its amount present.
- 5. $MoO₃$ enhanced the crystallization process of alumina into κ -Al₂O₃ at 700[°]C and α -Al₂O₃ phase at 900° C and 1000° C.

References

- [1] Y. Okamato, T. Shimokaws, T. Imanka, S. Teranshi, J. Catal. 57 (1979) 153.
- [2] P. Gajardo, P. Grang, B. Delmon, Surf. Interface Anal. 3 (1981) 206.
- [3] A. Lycourghiotis, D. Vattis, G. Karaiskadis, N. Katsons, J. Less-Common Met. 86 (1982) 137.
- [4] M. Lo Jacono, M. Schiavello, V.H.J. De Beer, G. Minell, J. Phys. Chem. 81 (1977) 1583.
- [5] R. Margraf, J. Leyrer, H. Knözinger, E. Taglauer, Surf. Sci. 189, 190 (1987) 842.
- [6] J. Leyrer, B. Vielhaber, M.I. Zaki, Mater. Chem. Phys. 13 (1985) 301.
- [7] Y.J. Liu, Y.C. Xie, J. Ming, J. Liu, Y.Q. Tang, Cuihua Xuebao 3 (1982) 262.
- [8] Y.J. Liu, Y.C. Xie, Li.Z.Y. Zou, Y.Q. Tang, Cuihua Xuebao 5 (1984) 262.
- [9] A.A. Ibrahim, G.A. El-Shobaky, Thermochim. Acta 147 (1989) 175.
- [10] J. Grimblot, E. Payen, Surf. Prop. Catal. Non-Metals 38 (1983) 189.
- [11] G.A. El-Shobaky, F.H.A. Abdalla, A.M. Ghazza, K.A. Khalil, Thermochim. Acta 275 (1996) 235.
- [12] G.A. El-Shobaky, G.A. Fagal, N.A. Hassan, Thermochim. Acta 311 (1998) 205.
- [13] H. Jeziorowski, H. Knözinger, J. Phys. Chem. 83 (1979) 1166.
- [14] R.C. Mckenzie, Scifax Differential Tehrmal Analysis Data Index, Cleaver-Hume, London, 1962.
- [15] G.W. Brindly, J.O. Choe, Am. Mineral 46 (1961) 771.
- [16] J. Zemlica, C. Barts, Krist Technol. 7 (1972) 965.
- [17] G.A. El-Shobaky, N.M. Ghoneim, E. Sultan, Thermochim. Acta 63 (1983) 39.
- [18] G.A. El-Shobaky, K.A. El-Barawy, F.H.A. Abdalla, Thermochim. Acta 96 (1985) 129.
- [19] G.A. El-Shobaky, G.A. Fagal, A.M. Dessouki, Egypt. J. Chem. 31(3) (1983) 317.
- [20] G.A. El-Shobaky, G.A. Fagal, N.H. Amin, Thermochim. Acta 141 (1989) 205.